



Product Information

Stablecote is a fast setting, rapid curing, 100% solids, flexible, aliphatic, two component spray polyurea with excellent color retention, that can be applied to suitably prepared interior or exterior concrete and metal surfaces. Its extremely fast gel time makes it suitable for applications down to - 20°F. It may be applied in single or multiple applications without appreciable sagging and is relatively insensitive to moisture and temperature allowing application in most temperatures. Stablecote offers a tack-free time of less than two minutes and exhibits 220% elongation upon curing with 50 Shore D hardness.

Features

- Color Retention
- Thermal Stability
- Elastomeric
- Seamless
- Meets USDA criteria
- Chemical Resistance
- Low Temperature Flexibility
- Abrasion and Impact Resistant

Packaging

10 Gallon Kit

5 Gallons Part-A (Isocyanate) and 5 Gallons Part-B (Resin)

100 Gallon Kit

50 Gallons Part-A (Isocyanate) and 50 Gallons Part-B (Resin)

Products are packaged by weight, so final package volume is a close estimation.

Limitations

Do not open until ready to use. Both Part-A and Part-B containers must be fitted with a desiccant device during use.

Colors

Clear/Neutral. Custom colors are available upon request. Color Packs, when used, must be added to Part-B.

Product Use

Applications

- Aliphatic Top Coat
- Cold Storage
- Warehouse Floors
- Water / Wastewater
- Structural Steel
- Food Facilities
- Parking Garage Deck
- Secondary Containment
- Manufacturing Facilities
- Mining Operations

Coverage Rate

Stablecote can be applied at any rate to achieve desired thickness. Theoretical coverage for 1 mil thickness is one gallon per 1600 sq. ft.

Physical Properties

Mix Ratio by Volume	1A : 1B
Pot Life @ 150F	10-15 Seconds
Tack Free Time	60-120 Seconds
Recoat Time	0-6 Hours
Hardness, ASTM D-2240	45 - 55 Shore D
Tensile Strength, ASTM D-412*	3000 - 3600 psi
Elongation, ASTM D-412*	200-240%
Tear Resistance, ASTM D412*	380-420 pli
Water Asorption, ASTM D471	<1.0

The values stated in this data sheet are produced under controlled laboratory conditions.

Safety and Storage

For in-depth information on product safety and precautions, please review the product SDS sheets. Prior to using the product, ensure that you have the proper personal protection equipment (PPE) available. This includes but is not limited to the following items:

- Safety Glasses with a splash shield
- Minimum Organic Cartridge Respirator
- Rubber or Nitrile Gloves
- Disposable or Reusable Long Sleeve Overalls
- Rubber or leather boots

Always be sure to follow the precautions listed below when using the material:

- Do Not use near high heat or open flame
- Do Not take internally
- Keep out of reach of children

Stablecote has a shelf life of twelve (12) months from date of manufacture, in factory-sealed containers. Part-A and Part-B drums must be stored above 60°F. Store drums on wooden pallets to avoid direct contact with the ground. If stored for a long period of time, rotate Part-A and Part-B drums regularly.

Installation

Both Side-A and Side-B materials should be preconditioned to 75-80°F before application. Recommended surface temperature must be at least 5°F above the dew point. StableCote should be applied using a plural component, heated, high pressure 1:1 spray mixing equipment. Both Part-A and Part-B materials should be sprayed at a minimum of 2000 psi and at temperatures above 150°F. Adequate pre pressure and temperature should be maintained at all times. StableCote should be sprayed in smooth, multidirectional passes to improve uniform thickness and appearance.

Product Mixing

Must be installed using a 1:1 ratio plural high-pressure, heated pump, fitted with high-pressure impingement mix spray gun. The proper necessary equipment can vary by the individual application. Contact American Manufactured Poly for more support. StableCote may not be diluted under any circumstances. Thoroughly mix Part-B (Resin side) with air driven power equipment until a homogeneous mixture and color is obtained.

Clean-Up / Disposal

Excess material can be mixed together at the proper ratio and disposed of without restriction once cured. Product containers may be disposed of according to local, state and federal laws.

Equipment should be cleaned with an environmentally safe, urethane-grade solvent (alcohol free) as permitted under local regulations immediately after use.

Technical Support

For technical support, please call 317-209-1111 Monday to Friday between the hours of 8am – 5pm EST. You may also send an email anytime to sales@mccind.com.

Warranty

At its sole election, American Manufactured Poly LLC (the company) will refund the price of or replace product it finds to be defective provided the product has been used properly and installed by a certified American Manufactured Poly LLC applicator. Except as expressly stated above, the company makes no warranty of merchantability and no warranty of fitness for any particular purpose; nor does it make any warranty, express or implied, of any nature whatsoever with respect to the product or its use. In no event shall the company be liable for delay caused by defects, loss of use, indirect, special or consequential damages, or for any charges or expenses of any nature incurred without its written consent.

Other Information

Warning - This product contains Isocyanates and Curative Material.

Distributed by:
MCC Equipment and Service Center
2705 E Main St
Plainfield IN 46168

317-209-1111

Email: sales@mccind.com
Web: www.mccind.com

Created Date: 04/01/2020

Revised Date: 04/01/2020

Notes: Not Available

