

MICRON CLEAN & SEAL – CERAMIC, PORCELAIN & QUARRY TILE

Category: Micron

System: Micron Clean & Seal - Ceramic, Porcelain & Quarry Tile

Product: NeverStrip Tile Seal

Surfaces: Ceramic, Porcelain, Quarry Tile



- 1)** Thoroughly strip and clean the substrate, so it is free of all wax, sealers, soil and greases.
- 2)** Apply Tile Seal onto a small area of the floor. If the sealer separates like oil and water or has fish-eyes, then the floor's surface tension will not allow the sealer's application. Unlike resilient flooring, typically these harder surfaces do not allow for the modification of the surface tension with a pad.
- 3)** Apply 2-3 applications of Tile Seal on ceramic, porcelain, and quarry tile. Two applications are acceptable if the sealer's appearance is attractive. The spread rate is 5,000 - 6,000 sq. feet per gallon per application on non-porous surfaces. The first application often has less coverage per gallon. Apply product with a flat microfiber pad and a trigger sprayer on a quart bottle or a standard garden pump up sprayer can be used. Avoid sprayers which introduce air under higher pressures. Apply a mist of product onto the section just before the product is spread with a standard microfiber pad. Do sections 3' x 4' or 3' x 5' at a time. If one person is spraying and one person is spreading, then the spraying should be "just before" the person spreads in the section. Do NOT apply too much product onto the floor. If the product is "White" when you spread the product, then there is too much of the sealer applied to the floor. Do NOT Pull Product from one section onto another. Do NOT overwork the product. Do spread product onto adjoining sections by a couple of inches to avoid skips. Do allow 10 to 15 minutes for the product to dry before applying the next application, to burnish, or to allow typical commercial traffic to resume.

Caution: Keep water off the floor for 8 hours.

An alternative application method is to use a [Spray Microfiber Floor Mop](#) with a quart bottle on the stem and a trigger at the top of the pole to release a spray in front of the microfiber pad. Typically, two sprays is an appropriate amount of sealer to spread across an area 18" wide and 36" forward.

Scrubbing the floor with a red pad and Micron Clean (2 oz./gallon of water), then burnishing during the first week or two after application is a best practice for removing marks/scuffs/surface scratches from the sealer during its initial curing.

Additional instructions on Product Data Sheets and other resources are available at www.neverstrip.com.

Cleaning and Maintenance: Click [here](#) for instructions.



neverstrip.com