

R35X

Patent Pending

FOIL / SCRIM / KRAFT

Meets ASTM C1136, Types II, IV
Tentative Specification

FACING COMPOSITION	DESCRIPTION	VALUES (ENGLISH)	VALUES (METRIC)
Foil	Aluminum	0.0003 inch	7.6 micron
Reinforcing	Tri-Directional Fiberglass	2 / inch (MD) 3 / inch (XD)	8 / 100 mm (MD) 12 / 100 mm (XD)
Adhesive	Flame Resistant		
Kraft	Natural	29 lbs/ 3000 ft ²	48 g / m ²

PHYSICAL PROPERTIES	TEST METHOD	VALUE (ENGLISH)	VALUES (METRIC)
Basis Weight	T 410	23 lbs/1000 ft ²	108 g/m ²
Permeance (WVTR)	ASTM E96 / Procedure A	0.02 perm	1.15 ng/Ns
Bursting Strength	ASTM D774	41 psi	2.8 kg/cm ²
Tensile Strength	ASTM C1136	37 lbs/inch width (MD) 24 lbs/inch width (XD)	6.5 kN/m (MD) 4.2 kN/m (XD)
Caliper/Thickness	T 411	0.008 inch	191 μm
Accelerated Aging	ASTM C1258 30 Days @ 95% RH, 120°F (49°C)	No Corrosion No Delamination	No Corrosion No Delamination
Low Temperature Resistance	ASTM C1263 -40°F (-40°C)	Remains Flexible No Delamination	Remains Flexible No Delamination
High Temperature Resistance	ASTM C1263 150°F (66°C)	Remains Flexible No Delamination	Remains Flexible No Delamination
Water Immersion	24 hours @ 73°F (23°C)	No Delamination	No Delamination
Mold Resistance	ASTM C665 / C1338	No Growth	No Growth
Dimensional Stability	ASTM D1204	0.50%	0.50%
Emissivity	ASTM E408	0.03	0.03

FIRE TESTING

	ASTM E84 / UL 723	
	Foil Side	Kraft Side
Flame Spread	0	25
Smoke Developed	0	10



Physical Properties based upon statistical averages. Weight/Thickness +/- 10%.

California Safe Drinking Water and Toxic Enforcement Act (Prop. 65): This product is exempt from labeling requirements under this Act.

Rev. 6, effective date 2/3/2021

506 North Street, Plymouth, IN 46563 U.S.A.
Phone: (574) 822-0100 | Fax: (574) 822-1144 | www.winonabp.com