

Columbia Architectural Products, Inc.

1" THERM-ALCLAD™ Insulated Glazing Panels

Product Data Sheet

Product Name:

1" Therm-Alclad™ Insulated Glazing Panels

Manufacturer:

Columbia Architectural Products, Inc. 10722 Tucker Street Beltsville, Maryland 20705 phone: (301) 937-4383 fax: (301) 937-6850 web: www.capmetalpanels.com

Panel Description:

Therm-Alclad[™] is our trade name for our light weight water impervious insulated glazing panels.

Available in various standard or custom configurations, smooth and stucco embossed finishes.

Therm-Alclad[™] panels provide a decorative, yet exceptional strong and durable, each panel weighs 1 1/2 pounds a square foot.

Therm-Alclad[™] panels are not damaged by water intrusion. Stock sizes are 48" widths x 96" & 120" lengths.

Stock CAP-Clad[™] Color Selection:



Actual Colors may vary from those shown above. Samples are available upon request. Call 866-583-2726



Panel Composition:

ion: d[™] panel has 3mm High Density

Our 1" Therm-Alclad[™] panel has 3mm High Density Polypropylene Eco-Poly Substrates, 5/8" EPS Foam Core and .040 Aluminum face and back, 4.75 R value.

Features & Benefits:

- Outstanding strength (Stronger than corrugated cores)
- Lighter than Competitive Panels
- Bi-directional Construction
- Eco Friendly
- 100% Recyclable Materials

Applications include:

 Fascias 	 In-Fill Panels 	 Signage
 Storefronts 	 Soffits 	 Trade show booths

Therm-Alclad[™] glazing panels can be cut on site with standard carpentry tools. All panels are masked to protect them throughout the installation process.

Our standard colors offer beauty and durability with coil coated Kynar 500[®] and Duracoat[®] polyester finishes. Kynar solid and metallic colors come with a 20 year finish warranty and while the Polyester finishes come with a 10 year finish warranty. All are painted finish options require little to no maintenance.

Technical data for Kynar 500[®] Coating on aluminum:

- Life Expectancy 20 years exposure: Chalk-rating 8 +
- ASTM G-23 Type EH Apparatus) Accelerated Weathering 5,000 hours: Chalk-rating 8 or better
- ASTM D 2794 Impact Resistance (1/2" ball indenter, Gardner Impact tester. No cracking or adhesion loss
- ASTM B 117 Salt Spray Resistance, 3000 hours
- ASTM D 1308 Chemical/Acid Pollution Resistance Pass
- ASTM D 968 Abrasion Resistance 65+ 10 liters

